

การพัฒนาฟิล์มบางทังสเตนออกไซด์ที่เจือด้วยไนโอเบียมสำหรับประยุกต์ใช้เป็นตัว  
ตรวจวัดแก๊สซัลเฟอร์ไดออกไซด์ในอุตสาหกรรมลำไยอบแห้ง

The Development of Niobium Doped Tungsten Oxide Thin Film for Application  
in Sulfur Dioxide Gas Sensor with Dried Longan Industry

วิรันธชา เครือฟู<sup>1</sup> และภูสิต ปุกมณี<sup>2</sup>

Viruntachar Kruefu<sup>1</sup> and Pusit Pookmancee<sup>2</sup>

<sup>1</sup>สาขาวิชาวัสดุศาสตร์ คณะวิทยาศาสตร์ มหาวิทยาลัยแม่โจ้ จ.เชียงใหม่ 50290

<sup>2</sup>สาขาวิชาเคมี คณะวิทยาศาสตร์ มหาวิทยาลัยแม่โจ้ จ.เชียงใหม่ 50290

บทคัดย่อ

ในการศึกษานี้ได้ทำการเตรียมอนุภาคนาโนทังสเตนออกไซด์บริสุทธิ์ และอนุภาคนาโนทังสเตนออกไซด์ ที่เจือด้วยไนโอเบียม ที่เตรียมด้วยวิธีไฮโดรเทอร์มอล เพื่อนำไปประยุกต์เป็นตัวตรวจจับแก๊ส โดยการเจือไนโอเบียมที่ความเข้มข้น 0.25, 0.50 และ 1.00 wt.% โดยทังสเตนออกไซด์ ถูกเตรียม ด้วยเทคนิคไฮโดรเทอร์มอล ที่ใช้สารละลายตั้งต้นโซเดียมทังสเตน และโซเดียมคลอไรด์ เตรียมฟิล์มเซินเซอร์โดยวิธีการหมุนเหวี่ยงสารบนอลูมินาซับสเตรท ที่ทำซ้ำไฟฟ้าด้วยทอง หาลักษณะเฉพาะด้วยเทคนิคการวิเคราะห์พื้นที่ผิวการดูดซับแก๊สในโตรเจน การวิเคราะห์การเลี้ยวเบนของรังสีเอ็กซ์ เทคนิคกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกราด เทคนิคกล้องจุลทรรศน์อิเล็กตรอนแบบส่องผ่าน และศึกษาผลของการเจือด้วยไนโอเบียมที่มีต่อความสามารถในการตรวจจับต่อแก๊สซัลเฟอร์ไดออกไซด์ แก๊สไฮโดรเจนซัลไฟด์ แก๊สไนโตรเจนไดออกไซด์ ไอของเอทานอล แก๊สไฮโดรเจน และแก๊สแอมโมเนีย ที่อุณหภูมิการทำงานของตัวตรวจจับแก๊ส 250–350°C ในสภาวะอากาศปกติ จากการทดลองพบว่าผลของการค่าการตอบสนองต่อแก๊สต่างๆ ขึ้นกับความเข้มข้นของไนโอเบียมที่เจือลงไป การตอบสนองต่อแก๊สไฮโดรเจนซัลไฟด์ และไอของเอทานอล มีการตอบสนองได้ดีที่ความเข้มข้นของไนโอเบียม 0.25 wt.% ในขณะที่ การตอบสนองต่อแก๊สไฮโดรเจน และแก๊สไนโตรเจนไดออกไซด์ มีการตอบสนองได้ดีที่ความเข้มข้นของไนโอเบียม 0.50 wt.% และแก๊สแอมโมเนีย มีการตอบสนองได้ดีที่ความเข้มข้นของไนโอเบียม 1.00 wt.% ดังนั้นสามารถสรุปได้ว่าการเจือไนโอเบียมสามารถมาประยุกต์ใช้เป็นตัวตรวจจับแก๊สได้ดียิ่งขึ้น

คำสำคัญ: ทั้งสदनออกไซด์ ไนโอเบียม ซัลเฟอร์ไดออกไซด์ เซ็นเซอร์แก๊ส ไฮโดรเทอร์มอล เฟลมสเปรย์ไพโร-  
ลิซิส



## ABSTRACT

In this work, the effect of Niobium (Nb) loading on the gas sensing performances of  $\text{WO}_3$  nanostructures prepared by hydrothermal synthesis is studied. Unloaded  $\text{WO}_3$  and 0.25-1.00 wt% Nb-loaded  $\text{WO}_3$  nanostructures were synthesized by hydrothermal synthesis using sodium tungsten dihydrate and sodium chloride as precursors under an acidic condition. Unloaded  $\text{WO}_3$  and Nb-loaded  $\text{WO}_3$  nanostructures were characterized by Brunauer-Emmett-Teller (BET analysis), X-ray diffraction (XRD), Scanning Electron Microscopy (SEM) and Transmission Electron Microscopy (TEM). Nb-loaded  $\text{WO}_3$  nanostructures were deposited on  $\text{Al}_2\text{O}_3$  substrate interdigitated with Au electrodes by spin-coating technique. Next, the  $\text{WO}_3$ -based gas sensors were characterized for gas-sensing towards  $\text{H}_2\text{S}$ ,  $\text{NO}_2$ ,  $\text{C}_2\text{H}_5\text{OH}$ ,  $\text{H}_2$  and  $\text{NH}_3$  at operating temperature ranging from 250-350 °C. The results showed that the effects of Nb loading on responses towards different gases depend considerably on the loading concentration. The response to  $\text{H}_2\text{S}$  and  $\text{C}_2\text{H}_5\text{OH}$ , are responding well to the intensity of Nb concentration of 0.25 wt.% while the response to  $\text{H}_2$  and  $\text{NO}_2$ , are responding well to the intensity of Nb concentration of 0.50 wt.% and  $\text{NH}_3$ , are responding well to the intensity of Nb concentration of 1.00 wt.%. Therefore, Nb loading concentration can be used to effectively tailor the gas-sensing performance of hydrothermally prepared  $\text{WO}_3$ -based gas sensors.

Hexagonal  $\text{WO}_3$  and Nb-loaded  $\text{WO}_3$  (Nb/ $\text{WO}_3$ ) nanorods were successfully synthesized by a simple hydrothermal process using sodium tungstate dihydrate ( $\text{Na}_2\text{WO}_4 \cdot 2\text{H}_2\text{O}$ ) and sodium chloride (NaCl) as initial precursors and further by the impregnation method using niobium (V) ethoxide. Phase, morphologies and particles size of the products were characterized by X-ray diffraction (XRD), High-resolution transmission electron microscopy (HRTEM) and Brunauer-Emmett-Teller (BET analysis).  $\text{WO}_3$  and Nb/ $\text{WO}_3$  films have been produced using spin-coating technique. The films were subsequently annealed at 450 °C for 3 h in air. The response of  $\text{WO}_3$  and Nb/ $\text{WO}_3$  sensors towards 20–500 ppm of  $\text{SO}_2$  in air was tested at the operating temperature ranging from 200-350 °C. It was found that 0.50 wt%Nb/ $\text{WO}_3$  sensing film showed higher response at 500 ppm  $\text{SO}_2$  (250 °C) than unloaded sample. Therefore, Nb loading concentration can be used to effectively tailor the gas-sensing performance of hydrothermally prepared  $\text{WO}_3$ -based  $\text{SO}_2$  gas sensors.

Key words:  $\text{WO}_3$ , niobium, sulfur dioxide, gas sensor, hydrothermal

